
SECTION 05 31 00
STEEL DECKING**PART 1 GENERAL****1.1 SECTION INCLUDES**

- A. Roof deck.
- B. Supplementary framing for openings up to and including 18 inches.
- C. Bearing plates and angles.

1.2 RELATED REQUIREMENTS

- A. Section 04 20 00 - Unit Masonry: Placement of anchors for bearing plates embedded in unit masonry assemblies.
- B. Section 04 26 00 - Single-Wythe Unit Masonry: Placement of anchors for bearing plates embedded in single-wythe masonry.
- C. Section 04 27 23 - Cavity Wall Unit Masonry: Placement of anchors for bearing plates embedded in cavity wall masonry.
- D. Section 05 21 00 - Steel Joist Framing: Placement of embedded steel anchors for bearing plates and joist seats in cast-in-place concrete.

1.3 REFERENCE STANDARDS

- A. ASTM A36/A36M - Standard Specification for Carbon Structural Steel; 2014.
- B. ASTM A653/A653M - Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process; 2015.
- C. AWS D1.1/D1.1M - Structural Welding Code - Steel; 2015.
- D. AWS D1.3/D1.3M - Structural Welding Code - Sheet Steel; 2008.
- E. IAS AC172 - Accreditation Criteria for Fabricator Inspection Programs for Structural Steel; International Accreditation Service, Inc; 2011.
- F. ICC-ES AC43 - Acceptance Criteria for Steel Deck Roof and Floor Systems; ICC Evaluation Service, Inc; 2010 (R2013).
- G. ICC-ES AC70 - Acceptance Criteria for Fasteners Power Driven into Concrete, Steel and Masonry Elements; ICC Evaluation Service, Inc; 2013.
- H. SDI (DM) - Publication No.30, Design Manual for Composite Decks, Form Decks, and Roof Decks; 2007.
- I. SSPC-Paint 20 - Zinc-Rich Primers (Type I, "Inorganic," and Type II, "Organic"); 2002 (Ed. 2004).

1.4 SUBMITTALS

- A. See Section 01 30 00 - Administrative Requirements, for submittals procedures.
- B. Product Data: Provide deck profile characteristics, dimensions, structural properties, and finishes.
- C. Shop Drawings: Indicate deck plan, support locations, projections, openings, reinforcement, pertinent details, and accessories.
- D. Certificates: Certify that products furnished meet or exceed specified requirements.
- E. Welders Certificates: Certify welders employed on the Work, verifying AWS qualification within the previous 12 months.
- F. Designer's Qualification Statement.
- G. Fabricator's Qualification Statement: Provide documentation showing steel fabricator is accredited under IAS AC172 and/or American Institute of Steel Construction (AISC) Certified.

1.5 QUALITY ASSURANCE

- A. Design deck layout, spans, fastening, and joints under direct supervision of a Professional Structural Engineer experienced in design of this work and licensed in Commonwealth of Pennsylvania.
- B. Fabricator Qualifications: A qualified steel fabricator that is accredited by the International Accreditation Service (IAS) Fabricator Inspection Program for Structural Steel in accordance with IAS AC172 and/or American Institute of Steel Construction (AISC) Certified.
- C. Installer Qualifications: Company specializing in performing the work of this Section with minimum 10 years of experience.

1.6 DELIVERY, STORAGE, AND HANDLING

- A. Cut plastic wrap to encourage ventilation.
- B. Separate sheets and store deck on dry wood sleepers; slope for positive drainage.

PART 2 PRODUCTS**2.1 MANUFACTURERS**

- A. Steel Deck:
 - 1. Canam Steel Corporation: www.canam-steeljoists.ws.
 - 2. Cordeck, Inc: www.cordeck.com/#sle.
 - 3. Nucor-Vulcraft Group: www.vulcraft.com/#sle.

2.2 STEEL DECK

- A. All Deck Types: Select and design metal deck in accordance with SDI Design Manual.
 - 1. Calculate to structural working stress design and structural properties specified.
 - 2. Maximum Vertical Deflection of Roof Deck: 1/240 of span.
 - 3. Maximum Lateral Deflection of Diaphragms: 1/500 of the height of the wall.
- B. Roof Deck: Non-composite type, fluted steel sheet:
 - 1. Galvanized Steel Sheet: ASTM A653/A653M, Structural Steel (SS) Grade 33/230, with G90/Z275 galvanized coating.
 - 2. Minimum Base Metal Thickness: 20 gage, 0.0359 inch.
 - 3. Nominal Height: 1-1/2 inch.
 - 4. Profile: Fluted; SDI NR.
 - 5. Formed Sheet Width: 24 inch.
 - 6. Side Joints: Lock seam.
 - 7. End Joints: Lapped, welded.

2.3 ACCESSORY MATERIALS

- A. Bearing Plates and Angles: ASTM A36/A36M steel, galvanized per ASTM A123/A123M.
- B. Welding Materials: AWS D1.1/D1.1M.
- C. Fasteners: Galvanized hardened steel, self tapping.
- D. Powder Actuated Mechanical Fasteners: Steel; with knurled shank and forged ballistic point. Comply with applicable requirements of ICC-ES AC70.
 - 1. Design Requirements: Provide number and type of fasteners that comply with the applicable requirements of SDI (DM) design method for roof deck and floor deck applications and ICC-ES AC43.

- E. Mechanical Fasteners: Steel; hex washer head, self-drilling, self-tapping.
 - 1. Design Requirements for Sidelap Connections: Provide number and type of fasteners that comply with the applicable requirements of SDI (DM)SDI design method for roof deck and floor deck applications and ICC-ES AC43.
 - 2. Fasteners for Exposed Steel Roof Deck Application: Manufacturer's standard stainless steel with bonded neoprene washer.
- F. Weld Washers: Mild steel, uncoated, 3/4 inch outside diameter, 1/8 inch thick.
- G. Touch-Up Primer for Galvanized Surfaces: SSPC-Paint 20, complying with VOC limitations of authorities having jurisdiction.
- H. Flute Closures: Closed cell foam rubber, 1 inch thick; profiled to fit tight to the deck.

2.4 FABRICATED DECK ACCESSORIES

- A. Sheet Metal Deck Accessories: Metal closure strips, wet concrete stops, and cover plates, 22 gage, 0.0299 inch thick sheet steel; of profile and size as indicated; finished same as deck.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Verify existing conditions prior to beginning work.

3.2 INSTALLATION

- A. Erect metal deck in accordance with SDI Design Manual and manufacturer's instructions. Align and level.
- B. On concrete and masonry surfaces provide minimum 4 inch bearing.
- C. On steel supports provide minimum 1-1/2 inch bearing.
- D. Fasten deck to steel support members at ends and intermediate supports at 12 inches on center maximum, parallel with the deck flute and at each transverse flute using methods specified.
 - 1. Welding: Use fusion welds through weld washers.
- E. Clinch lock seam side laps.
- F. At mechanically fastened male/female side laps fasten at 24 inches on center maximum.
- G. Drive mechanical sidelap connectors completely through adjacent lapped sheets; positively engage adjacent sheets with minimum three-thread penetration.
- H. At welded male/female side laps weld at 18 inches on center maximum.
- I. Weld deck in accordance with AWS D1.3/D1.3M.
- J. See structural drawings for steel angle reinforcement sizes at deck openings.
- K. At openings between deck and walls, columns, and openings, provide sheet steel closures and angle flashings to close openings.
- L. Close openings above walls and partitions perpendicular to deck flutes with single row of foam cell closures.
- M. Immediately after welding deck and other metal components in position, coat welds, burned areas, and damaged surface coating, with touch-up primer.

END OF SECTION 05 31 00