

**SECTION 06 83 16**  
**FIBERGLASS REINFORCED PANELING**

**PART 1 GENERAL**

**1.1 SECTION INCLUDES**

- A. Fiberglass reinforced plastic panels.
- B. Trim.

**1.2 REFERENCE STANDARDS**

- A. 9 CFR 416.2 - Regulatory Requirements Under the Federal Meat Inspection Act and the Poultry Products Inspection Act, Part 416-Sanitation current edition.
- B. ASTM D5319 - Standard Specification for Glass-Fiber Reinforced Polyester Wall and Ceiling Panels 2017.
- C. ASTM E84 - Standard Test Method for Surface Burning Characteristics of Building Materials 2022.

**1.3 SUBMITTALS**

- A. Product Data: Provide data on specified products, describing physical and performance characteristics; including sizes, patterns and colors available; and installation instructions.
- B. Samples: Submit two samples 3 by 3 inch in size illustrating material and surface design of panels.

**1.4 DELIVERY, STORAGE, AND HANDLING**

- A. Store panels flat, indoors, on a clean, dry surface. Remove packaging and allow panels to acclimate to room temperature for 48 hours prior to installation.

**PART 2 PRODUCTS**

**2.1 MANUFACTURERS**

- A. Fiberglass Reinforced Plastic Panels:
  - 1. Crane Composites, Inc: [www.cranecomposites.com/#sle](http://www.cranecomposites.com/#sle).
  - 2. Marlite, Inc: [www.marlite.com/#sle](http://www.marlite.com/#sle).
  - 3. Nudo Products, Inc: [www.nudo.com/#sle](http://www.nudo.com/#sle).
  - 4. Panolam Industries International, Inc: [www.panolam.com/#sle](http://www.panolam.com/#sle).
  - 5. Substitutions: Or equal as approved by the Professional.

**2.2 PANEL SYSTEMS**

- A. Wall Panels:
  - 1. Panel Size: 4 by 8 feet.

2. Panel Thickness: 0.09 inch.
3. Surface Design: Embossed.
4. Color: As selected by Architect.
5. Attachment Method: Adhesive only, with trim and sealant in joints.

## **2.3 MATERIALS**

- A. Panels: Fiberglass reinforced plastic (FRP), complying with ASTM D5319.
  1. Surface Burning Characteristics: Maximum flame spread index of 25 and smoke developed index of 450; when system tested in accordance with ASTM E84.
  2. Sanitation and Cleanability: Comply with 9 CFR 416.2.
- B. Trim: Vinyl; color coordinating with panel.
- C. Adhesive: Type recommended by panel manufacturer.
- D. Sealant: Type recommended by panel manufacturer; color matching panel.

## **PART 3 EXECUTION**

### **3.1 EXAMINATION**

- A. Verify existing conditions and substrate flatness before starting work.
- B. Verify that substrate conditions are ready to receive the work of this section.

### **3.2 INSTALLATION - WALLS**

- A. Install panels in accordance with manufacturer's instructions.
- B. Cut and drill panels with carbide tipped saw blades, drill bits, or snips.
- C. Apply adhesive to the back side of the panel using trowel as recommended by adhesive manufacturer.
- D. Apply panels to wall with seams plumb and pattern aligned with adjoining panels.
- E. Install panels with manufacturer's recommended gap for panel field and corner joints.
- F. Place trim on panel before fastening edges, as required.
- G. Fill channels in trim with sealant before attaching to panel.
- H. Install trim with adhesive and screws or nails, as required.
- I. Seal gaps at floor, ceiling, and between panels with applicable sealant to prevent moisture intrusion.
- J. Remove excess sealant after paneling is installed and prior to curing.

**END OF SECTION**