

SECTION 096500 RESILIENT FLOORING

PART 1 GENERAL

1.01 SECTION INCLUDES

- A Resilient tile flooring.
- B Resilient base.
- C Installation accessories.

1.02 REFERENCE STANDARDS

- A ASTM F1066 - Standard Specification for Vinyl Composition Floor Tile 2004 (Reapproved 2018).
- B ASTM F1861 - Standard Specification for Resilient Wall Base 2021.

1.03 SUBMITTALS

- A Product Data: Provide data on specified products, describing physical and performance characteristics; including sizes, patterns and colors available; and installation instructions.
- B Selection Samples: Submit manufacturer's complete set of color samples for Architect's initial selection.
- C Maintenance Data: Include maintenance procedures, recommended maintenance materials, and suggested schedule for cleaning, stripping, and re-waxing.
- D Maintenance Materials: Furnish the following for Owner's use in maintenance of project.
 - 1. Extra Flooring Material: 20 square feet of each type and color.

1.04 QUALITY ASSURANCE

- A Manufacturer Qualifications: Company specializing in manufacturing specified flooring with minimum three years documented experience.
- B Installer Qualifications: Company specializing in installing specified flooring with minimum three years documented experience.

1.05 DELIVERY, STORAGE, AND HANDLING

- A Upon receipt, immediately remove any shrink-wrap and check materials for damage and the correct style, color, quantity and run numbers.
- B Store all materials off of the floor in an acclimatized, weather-tight space.
- C Maintain temperature in storage area between 55 degrees F and 90 degrees F.

1.06 FIELD CONDITIONS

- A Store materials for not less than 48 hours prior to installation in area of installation at a temperature of 70 degrees F to achieve temperature stability. Thereafter, maintain conditions above 55 degrees F.

PART 2 PRODUCTS

2.01 TILE FLOORING

- A Vinyl Composition Tile: Homogeneous, with color extending throughout thickness.
 - 1. Manufacturers:
 - a. Armstrong Flooring; Standard Execelon Imperial Texture:
www.armstrongflooring.com/#sle.

- b. Johnsonite, a Tarkett Company: www.johnsonite.com/#sle.
 - c. Or Approved Equal.
- 2. Minimum Requirements: Comply with ASTM F1066, of Class corresponding to type specified.
- 3. Size: 12 by 12 inch.
- 4. Thickness: 0.125 inch.
- 5. Color: To be selected by Architect from manufacturer's full range.

2.02 RESILIENT BASE

- A Resilient Base: ASTM F1861, Type TS, rubber, vulcanized thermoset; Style B, Cove.
 - 1. Manufacturers:
 - a. Johnsonite, a Tarkett Company: www.johnsonite.com/#sle.
 - b. Mannington Commercial: www.manningtoncommercial.com/#sle.
 - c. Roppe Corporation: www.roppe.com/#sle.
 - 2. Height: 4 inches.
 - 3. Thickness: 0.125 inch.
 - 4. Finish: Satin.
 - 5. Length: Roll.
 - 6. Color: To be selected by Architect from manufacturer's full range.
 - 7. Accessories: Premolded external corners.

2.03 ACCESSORIES

- A Subfloor Filler: White premix latex; type recommended by adhesive material manufacturer.
- B Primers, Adhesives, and Seam Sealer: Waterproof; types recommended by flooring manufacturer.
- C Moldings, Transition and Edge Strips: Same material as flooring.
- D Sealer and Wax: Types recommended by flooring manufacturer.

PART 3 EXECUTION

3.01 EXAMINATION

- A Verify that surfaces are flat to tolerances acceptable to flooring manufacturer, free of cracks that might telegraph through flooring, clean, dry, and free of curing compounds, surface hardeners, and other chemicals that might interfere with bonding of flooring to substrate.
- B Verify that wall surfaces are smooth and flat within the tolerances specified for that type of work, are dust-free, and are ready to receive resilient base.
- C Cementitious Subfloor Surfaces: Verify that substrates are ready for resilient flooring installation by testing for moisture and alkalinity (pH).
 - 1. Obtain instructions if test results are not within limits recommended by resilient flooring manufacturer and adhesive materials manufacturer.

3.02 PREPARATION

- A Prepare floor substrates as recommended by flooring and adhesive manufacturers.
- B Remove subfloor ridges and bumps. Fill minor low spots, cracks, joints, holes, and other defects with subfloor filler to achieve smooth, flat, hard surface.

- C Prohibit traffic until filler is fully cured.
- D Clean substrate.
- E Apply primer as required to prevent "bleed-through" or interference with adhesion by substances that cannot be removed.

3.03 INSTALLATION - GENERAL

- A Starting installation constitutes acceptance of subfloor conditions.
- B Install in accordance with manufacturer's written instructions.
- C Adhesive-Applied Installation:
 - 1. Spread only enough adhesive to permit installation of materials before initial set.
 - 2. Fit joints and butt seams tightly.
 - 3. Set flooring in place, press with heavy roller to attain full adhesion.
- D Where type of floor finish, pattern, or color are different on opposite sides of door, terminate flooring under centerline of door.
- E Install edge strips at unprotected or exposed edges, where flooring terminates, and where indicated.
 - 1. Resilient Strips: Attach to substrate using adhesive.
- F Scribe flooring to walls, columns, cabinets, floor outlets, and other appurtenances to produce tight joints.

3.04 INSTALLATION - TILE FLOORING

- A Mix tile from container to ensure shade variations are consistent when tile is placed, unless otherwise indicated in manufacturer's installation instructions.
- B Lay flooring with joints and seams parallel to building lines to produce symmetrical pattern.
- C Install square tile to ashlar pattern. Allow minimum 1/2 full size tile width at room or area perimeter.

3.05 INSTALLATION - RESILIENT BASE

- A Fit joints tightly and make vertical. Maintain minimum dimension of 18 inches between joints.
- B Miter internal corners. At external corners, use premolded units. At exposed ends, use premolded units.
- C Install base on solid backing. Bond tightly to wall and floor surfaces.

3.06 CLEANING

- A Remove excess adhesive from floor, base, and wall surfaces without damage.
- B Clean in accordance with manufacturer's written instructions.

3.07 PROTECTION

- A Prohibit traffic on resilient flooring for 48 hours after installation.

END OF SECTION