


INTERIOR ELEVATION

SCALE: 1/4" = 1'-0"

ROOM NO: 152A

3



2 CONC. REPAIR DETAIL @ EXISTING RAILING
SCALE: 3" = 1'-0"

CONCRETE REPAIR NOTES (SMALL AREAS):

1. AREA TO BE REPAIRED MUST BE CLEAN, SOUND AND FREE OF CONTAMINANTS. ALL LOOSE AND DETACHED CONCRETE SHALL BE REMOVED BY MECHANICAL MEANS. CONCRETE TO REMAIN MUST BE SOUND AND ROUGHENED TO PROMOTE MECHANICAL ADHESION.
2. SUBSTRATE SHALL BE SATURATED SURFACE DRY (SSD) WITH NO STANDING WATER DURING APPLICATION.
3. APPLY Sika AIRMATIC 110 EPICUREN TO PRIME THE SURFACE.
4. WHILE BONDING AGENT IS STILL WET, APPLY Sika TOP 123 PLUS.
5. FOR APPLICATIONS GREATER THAN 1 1/2" IN DEPTH, APPLY Sika TOP 123 PLUS IN LIFTS. SCORE THE TOP SURFACE OF EACH LIFT TO PROVIDE ROUGHENED SURFACE FOR NEXT LIFT/AO PRECEDING LIFT TO REACH FINAL SET.
6. APPLY TWO (2) COATS OF SikaBOND 870W TO SURFACES TO BE EXPOSED TO VIEW.

(SIKA IS MANUFACTURER FOR DESIGN BASIS. EQUAL MANUFACTURER MAY BE SUBMITTED FOR APPROVAL.)

ALL DIMENSIONS AND EXISTING CONDITIONS
shall be CHECKED and VERIFIED
by the CONTRACTOR at the SITE.

JOB NO.: 23001.00

DRAWN BY: JFS

DATE: 04.12.24

A-A2